



B-s1-d0 fire rated modified plywood

Innovation that challenges flames



-  FIRE RETARDANT EVEN AFTER SANDING OR MACHINING
-  SUSTAINABLE EUROPEAN PLANTATION WOOD
-  LIGHTWEIGHT & EASY-TO-MACHINE
-  STABILITY & DIMENSIONAL UNIFORMITY



The mark of
responsible forestry
This logo only refers
to FSC MIX CREDIT
products



garnica

Challenge the ordinary



B-s1-d0 fire rated modified plywood

Innovation that challenges flames

Finishes available:



Product description:

Plywood modified by an innovative treatment that renders the entire panel exceptionally fire resistant, certified by the most demanding tests even after sanding or machining.

Wide variety of formats available to suit any type of project.

Maximum sustainability and lightness due to its composition based on fast growing European plantation wood.

Glue Type: Class I (interior) according to the rule EN 636

Emission: Class E1 according to the rule EN 13986. CARB Phase 2 Low Formaldehyde Emission (on demand)

Quality faces: BB/BB

Applications/Uses:

Ideal panel for construction projects of restaurants, auditoriums, schools and other public buildings. B-s1-d0 and ASTM E-84 Euroclass certifications that prove its excellent performance in fire resistance tests.



Formats

Dimensions mm	2500x1220								
Thickness mm	9	10	12	15	18	21	25	30	40
No. of plies	5	7	7	9	9	11	13	15	19
Dimensions mm	3100x1530								
Thickness mm	9	12	15	18	21	25	30	40	
No. of plies	5	7	9	9	11	13	17	19	

Formats may vary without notice. Please contact your local sales manager to check the availability in your region.

Technical features

	Values	Standard
Density (Kg/m ³)	460-520	UNE EN 323
MOE - Modulus of elasticity (N/mm ²)	3.400-4.700	UNE EN 310
Face Screw Holding (kgf)	135	UNE EN 320
Moisture content (%)	6-14	UNE EN 322

Wood is a natural material and as such is unique in appearance & so often has naturally occurring variations in color, texture and grain pattern. The photographic reproductions used simply provide an example of a product's appearance & may not be representative of the full range of color, texture and grain variations. The data provided in this product specification should be used solely as a guide & is of no contractual value. It is the responsibility of the acquirer to determine if the product is suitable for the required application, to ensure that both the place & form of use are appropriate & in accordance with the manufacturer's requirements & recommendations & is in line with current regulations.



ASTM E-84 Class A

CARB Phase 2 **CE 2+** **CE**

garnica

Challenge the ordinary

Parque de San Miguel, 10 - bajo
26007 Logroño, La Rioja
Spain
Tel.: +34 941 51 23 55
Fax: +34 941 51 23 57
sales@garnica.one
www.garnica.one